

Garia® 405 M-32

Neat cutting oils

DESCRIPTION

Garia 405 M-32 is a neat cutting oil for general machining on automatic lathes, gear hobbing and on thread- or tooth-flank grinding machines. **Garia 405 M-32** is particularly good for working on middle to high resistance alloyed and low carbon steels and aluminum or magnesium alloys.

FEATURES / BENEFITS

Garia 405 M-32 is based on hydro treated mineral oils with a low aromatic content.

Combinations of polar, extreme pressure and anti wear additives provide the oil with high load carrying properties. The oil provide good tool life and good surface finish of the machined work pieces. High efficient anti mist additives reduce the mist load in the air.

Due to the active sulphur in the **Garia 405 M-32** there is a risk of staining of yellow metals.

Garia 405 M-32 is free of chlorine and heavy metals.

- Outstanding cleaning capability for optimal soil removal.
- May be used at ambient temperatures to dramatically reduce energy costs.
- Imparts corrosion inhibition to parts to protect them from rusting between operations thereby reducing scrap rates.

DATA (TYPICAL VALUES)

Appearance	Yellow
Kinematic viscosity @ 40 °C mm ² /s (ASTM D 7042)	32
Density @ 20° C kg/m ³ (DIN EN ISO 12185)	875
Flash point COC °C (DIN EN ISO 2592)	204
Cu-Corrosion Test Alfa (ASTM D 130)	4a

HEALTH AND SAFETY

Refer to SDS for proper handling and disposal. Please note that the SDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local Houghton representative.

NOTE: Read and understand all precautions on container labels before using this product.

HL 13.12 US



Houghton International Inc.
Madison and Van Buren Aves.
P. O. Box 930
Valley Forge, PA 19482-0930

Phone: 610-666-4000
Fax: 610-666-0174
info@houghtonintl.com
www.houghtonintl.com

This document contains information based on data that is believed to be correct. However, the product may not be applicable to all uses and operating environments. No warranty or guarantee is expressed or implied.